

GBAR Trap Meeting

Seoul National University

29.Nov.2019

9.1 Information on basic physical and chemical properties

Appearance: Semi-solid yellow/brown grease.

Odour: None.

pH: Not applicable.

Melting point: 42 to 52°C.

Initial boiling point and boiling range: >450°C.

Flash point: >200°C.

Flammability (solid, gas): Data not available.

Upper/lower flammability or explosive limits: Data not available.

Vapour pressure: 6×10^{-10} Torr at 20°C.

Vapour density: Not applicable.

Relative density: 0.911 at 20°C.

Water solubility: Insoluble.

Solubility: Soluble in aromatic hydrocarbon solvents.

서울대학교

ATTN.: 김 선기 교수님 / 원 동환님 귀하

TEL : 010-5168-9029, crowclaw@naver.com FAX :

견적 NO. : 2019 - 494

견적일자 : 2019. 11. 20.

주식회사 에스 크

대표이사 김 홍

경기 안양 동안 시민대로 161 안양무역센터 1102호

사업자등록번호 214-87-13973



아래와 같이 견적합니다.

품 명 및 규 격	수 량	단 가	금 액
1 Apiezon grease - type N	1	350,000	₩350,000

Line No.	Part Number	Description	Qty.	Unit Price	Discount	Amount
1	783001-8192	PXIe-8840, PXI-8840 및 PXIe-8821용 8GB RAM	1	1,058,400 952,560	10.00%	952,560
		본 제품에 대한 서비스 세부사항 하드웨어용 NI 스탠다드 서비스 프로그램 (SSP) Duration 3 Year(s)				
Sub Total:						952,560 KRW
V.A.T:						95,256 KRW
Total:						1,047,816 KRW

No.	품 명	수량	단 가	공급가액	부가세
1.	COOLCAT 2 NW Multi Layer Superinsulation	1	₩6,600,000	₩6,600,000	₩660,000
	- 10 layers of 6 micron polyester foil, both side aluminized at 400 Å, perforated				
	- 10 layers of non-woven polyester spacer material. The insulation is ultrasonic spot-welded to hold the foils together				
	- Interleaved with polyester non-woven spacer at 14~15 g/m2				
	- 1.5m wide x 50m long				
2.	COOLCAT 2 NW sheets	1	₩1,090,000	₩1,090,000	₩109,000
	- 10 layers of 6 micron polyester foil, both side aluminized at 400 Å, perforated				
	- Interleaved with polyester non-woven spacer at 14~15 g/m2				
	- 3m x 1.5m				
	* 납기 : 발주 후 6주 이내				
	* 결제 : 납품 후 100% 현금결제				
소 계				₩7,690,000	₩769,000
합 계				₩8,459,000	